

Material Data Sheet

Technical Sales

Copper

Material designation:	EN-Material No.	DIN-Material-No.
	CW008A [Cu-OF]	2.0040

Scope

This data sheet applies to flat and long products made of copper CW008A.

Application

The material CW008A has low strength values and shows a good weldability. Pure copper has good corrosion resistance in natural atmosphere. Due to its high degree of purity, CW008A has a very high electrical conductivity and is not susceptible to hydrogen embrittlement. In addition, pure copper has very good formability. This material is used when high electrical is required (electrical engineering).

Chemical composition in %

Cu	Bi	O	Pb
≥99,95 ^{a)}	≤0,0005	^{c)}	≤0,005

Other elements^{b)}: total: max. 0,03 %

^{a)} including silver, up to a maximum of 0,015 %

^{b)} The total of other elements (than copper) is defined as the sum of Ag, As, Bi, Cd, Co, Cr, Fe, Mn, Ni, O, P, Pb, S, Sb, Se, Si, Sn, Te und Zn, subject to the exclusion of any individual elements indicated.

^{c)} The oxygen content shall be such that the material conforms to the hydrogen embrittlement requirements of EN 1976

Mechanical properties at room temperature (rod, bar and wire) acc. to EN 13601

Temper	Dimensions			Hardness		Tensile strength	Proof strength	Elongation	
	round, square, hexagonal [mm]	Dicke [mm]	Breite [mm]	Brinell HBW	Vickers HV	R _m [N/mm ²]	R _{p0,2} [N/mm ²]	A _{100 mm} [%]	A [%]
D	2-160	0,5-40	1-200	as manufactured					
H035	2-160	0,5-40	1-200	35-65	35-65	-	-	-	-
R200	2-160	1-40	5-200	-	-	≥200	120	≥25	≥35
H065	2-80	0,5-40	1-200	65-60	70-95	-	-	-	-
R250	2-10	1-10	5-200	-	-	≥250	≥200	≥8	≥12
R250	>10-140	>10-40	>10-200	-	-	≥250	≥180	-	≥15
R230	>30-80	>10-40	>10-200	-	-	≥230	≥160	-	≥18
H085	2-40	0,5-20	1-120	85-110	90-115	-	-	-	-
H075	>40-80	>20-40	>20-160	75-100	80-105	-	-	-	-
R300	2-20	1-10	5-120	-	-	≥300	≥260	≥5	≥8
R280	>20-60	>10-20	>10-160	-	-	≥280	≥240	-	≥10
R260	>40-60	>20-40	>20-160	-	-	≥260	≥220	-	≥12
H100	2-10	0,5-5	1-120	≥100	≥110	-	-	-	-
R350	2-10	1-5	5-120	-	-	≥350	≥320	≥3	≥5

Mechanical properties at room temperature (tubes) acc. to EN 13600

Temper	Wall thickness t [mm]	Proof strength R _{p0,2} [N/mm ²]	Tensile strength R _m [N/mm ²]	Elongation A _{100 mm} [%]	Hardness	
					HBW	HV
D	all	cold drawn, without defined mechanical properties				
H035	≤40	-	-	-	35-60	35-65
R200	≤40	≤120	200-250	≥35	-	-
H065	≤20	-	-	-	60-90	65-95
R250	≤20	≥150	250-300	≥15	-	-
H090	≤10	-	-	-	85-105	90-110
R290	≤10	≥250	290-360	≥5	-	-
H100	≤5	-	-	-	≥95	≥100
R360	≤5	≥320	≥360	(≥3) ^{a)}	-	-

^{a)} The number in brackets is not a requirement of the standard, but is provided for information purpose only

Mechanical properties at room temperature (plate, sheet and strip) acc. to EN 13599

Temper	Thickness t [mm]	Proof strength R _{p0,2} [N/mm ²]	Tensile strength R _m [N/mm ²]	Elongation A _{50 mm} For thicknesses from 0,1 mm up to and including 2,5 mm [%]	A _{50 mm} For thicknesses > 2,5 mm [%]	Hardness HV
M	10-25	as manufactured				
H035	0,10-5	-	-	-	-	40-65
R220		(≤140)	220-260	≥33	≥42	-
H040	0,20-10	-	-	-	-	40-65
R200		(≤100)	200-250	-	≥42	-
H065	0,10-10	-	-	-	-	65-95
R240		≥180	240-300	≥8	≥15	-
H090	0,10-10	-	-	-	-	90-110
R290		≥250	290-360	≥4	≥6	-
H110	0,10-2	-	-	-	-	≥110
R360		≥320	≥360	≥2	-	

Reference data for some physical properties (for guidance only)

Density at 20 °C [kg/dm ³]	Electrical conductivity [MS/m]	Thermal Conductivity [W/m•K]	Specific heat capacity [J/Kg•K]	Young's modulus [MPa]	Shear modulus [MPa]
8,94	58,0	394	394	127000	-

Guidelines on the temperatures for hot forming and heat treatment

Soft annealing temperature	Stress-relieving annealing Temperature	Hot forming temperature
250-500 °C	150-200 °C	750-950 °C

Processing/Welding

The material has a very good cold formability. Furthermore, CW004A is suitable for welding and brazing. The machinability of this materials is rated as moderate to difficult. Machinability improves with increasing mechanical strength.

Remark

The material is compliant to RoHS and REACH.

Editor

tk accelis Materials GmbH
Technical Sales
thyssenkrupp Allee 1
45143 Essen
Germany

Reference

DIN EN 13599 : 2014-12	DIN Media GmbH, D-10772 Berlin
DIN EN 13600 : 2022-08	
DIN EN 13601 : 2021-07	
Kupfer-Datenblätter	Deutsches Kupferinstitut Berufsverband e.V. D-40239 Düsseldorf

Important note

Information given in this data sheet about the condition or usability of materials respectively products are no warranty for their properties, but act as a description.

The information, we give on for advice, comply to the experiences of the manufacturer as well as our own. We cannot give warranty for the results of processing and application of the products.