

## SFB-13 TDS

Property	Test Method	Value	Unit
Transmittance	ASTM E 424 1971 6. 5. 2	13	%
Tensile Strength (warp/weft)	ISO 13934-1:1999 C.R.E.STRIP METHOD	921.8 640.0	N/5cm
Tearing Strength (warp/weft)	ISO 13937-2:2000 C.R.E. SINGLE TONGUE METHOD	46.1 49.6	N
Elongation (warp/weft)	ISO 13934-1:1999 C.R.E.STRIP METHOD	23.6 29.1	%
Adhesion Strength (warp/weft)	ISO 2411:1991 C.R.E	108 88	N/5cm
Flexing Endurance	DIN 53351, FLEXOMETER METHOD	10	CYCLES
Resistance to Low Temp. (warp/weft)	ISO 13934-1:1999 -20°C, 5HRS	97.1 98.1	%
Resistance to High Temp. (warp/weft)	ISO 13934-1:1999 80°C, 5HRS	96.3 97.7	%
Colorfastness to Weathering	ASTM G 26, METHOD A, TYPE B	4	grade

For more information, visit our website at  
[www.star-flex.com](http://www.star-flex.com)