

SFF-1518 TDS

Property	Test Method	Value	Unit
Weight		510	g/m ²
Tensile Strength (warp/weft)	ISO 13934-1 : 2013 C.R.E.STRIP METHOD	2200 2000	N/50mm
Tearing Strength (warp/weft)	ISO 13937-2 : 2000 C.R.E. SINGLE TONGUE METHOD	160 170	N
Elongation (warp/weft)	ISO 13934-1 : 2013 C.R.E.STRIP METHOD	20 23.5	%
Adhesion Strength (warp/weft)	ISO 2411 : 2000 C.R.E	46 35	N/50mm
Flexing Endurance	DIN 53351 TEST CONDITION : -20°C, 400 CYCLES	No Change	Appearance

For more information, visit our website at
www.star-flex.com